Bricklayers White Cement		
Standard		Туре
AS 1316-2003 Physical Properties		Masonry Composite Cement Typical Results
Air Content	%	15
Water Retention	%	75
Fineness (Blaine)	m /kg	400
Density	g/cm	3.1
Initial Setting Time	minutes	140
Final Setting Time	minutes	170
Compressive Strength		AS 1316-2003
7 days	MPa	22
28 days	MPa	31

LaMaCo LaMaCo System Sdn Bhd

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong, 05150 Alor Setar, Kedah. Malaysia Tel : +60-4-771 1111 Fax : +60-4-772 4444 Http : www.lamaco.com Email : info@lamaco.com

- **Important 1:** While the information and data sheet contained in this promotional literature are presented in good faith and believed to be reliable, they do not constitute a part of our terms and conditions of sales unless specifically incorporated in our Order acknowledgement. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data sheet are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data sheet or products can be used without infringing patent of third parties.
- Important 2: LaMaCo Malaysia products are not guaranteed against defective materials and manufacture & are sold subject to its standard Terms & Conditions of sale, copies of which may be obtained on request. Whilst LaMaCo Malaysia endeavors to ensure that any advice, recommendation, specification or information is accurate and correct, it cannot- because it has no direct or continuous control over where or how its products are applied accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance any advice, specification, recommendation or information given by it.

Health & Safety Some of the components of this product may be hazardous during mixing and application. Please consult the relevant Health & Safety Data Sheets, available from LaMaCo Malaysia on request and sent with each delivery.