Urethane Alkyd Impregnation Enamel Sealer Protection for Concrete, All Types of Natural Mineral Stone/Slate & Masonry

Type: Solvent Base, Liquid Form

Characteristics

Top Gard 7388, is a solvent base urethane alkyd enamel concentrate that is based on modified with linoleic rich fatty is organic solvents.

Top Gard 7388, in organic solvents serve as high-quality general purposes water repellents (hydrophobic) for impregnating enamel sealer and priming mineral and highly alkaline substrates.

Features

- Good Depth of Penetration & Stop Diffusion of Vapour
- * Marine Environment
- * Excellent Protect of Chloride Attack
- * Excellent Protect of Freeze Thaw Cycles
- Excellent Protect of High Alkaline Resistance
- Tack-Free Drying
- * Effective even on Damp Substrates
- Water Repellency Develops Fast

After application **Top Gard 7388** reacts with the atmosphere moisture or pore water in the substrate, thereby generating the active ingredient while liberating alcohol. The active ingredient greatly lowers the water absorbency of the substrate. Since neither pores nor capillaries are clogged, the substrate retains a very high degree of water vapour permeability.

Uses

Top Gard 7388 is suitable for imparting water repellency to absorbent, porous, mineral construction materials,

- * All kinds of concrete for <u>Buildings</u>, <u>Reservoirs</u>, <u>Jetties & Bridges</u>
- Brickwork Surfaces
- Mineral-based natural and artificial stone
- * Aerated concrete
- * Sand-lime brickwork
- * Cement fiberboards
- * Mineral paints
- * Cement sand or mineral plasters

Top Gard 7388 is also suitable as primer for exterior paints. **Top Gard 7388** is not suitable for rendering gypsum water repellent.

Surface Preparation

The surface to be applied with **Top Gard 7388** shall be free of dust and dirt. Lime efflorescence, salt and paint remnants, etc must be removed, preferably by high pressure water-jet, hot water or pressurized steam. Detergent cleaning is not recommended as if detergents are not removed completely, they can adversely affect the water repellency effect. Acid or alkali cleaning is also not recommended because of the risk of damaging the mortar joint or formation of salts which would lead to efflorescence.

The best impregnation effect is achieved on a dry, very absorbent surface, although **Top Gard 7388** can also be successfully employed on slightly damp surfaces (moisture content should not be more than 10 % by volume).

If there are joints to be filled on concrete surfaces which have been impregnated with **Top Gard 7388** for example precast concrete elements, adhesion to these penetrable surfaces will not be impaired. The relevant primers must always be used, followed on with suitable sealants, for example Flex Joint V or Flex Joint H.

Technical Specification (2 Grades)

Product Data		Top Gard 7388 Std	Top Gard 7388 HP
Appearance		Colorless	Colorless
Silane / siloxane content ,approx	(%)	3.50	12.00
Specific Gravity at 25 °C, approx	g/cm³	0.92 (±0.01)	0.92 (±0.01)
Viscosity at 25°C, approx	(mm²/s)	70 (±10)	67 (±10)
Flash point, (DIN EN ISO 2719) approx	(°C)	80	65
Reduction of water absorption	(%)	90.50	97.50
Water absorption	(%)	<9.50	<2.50
Reduction of chloride ion content	(%)	81.00 (no corrosion)	85.00 (no corrosion)
Water vapour transmission	(%)	>100	>110
Penetration Depth (Concrete G 30)	(mm)	>1.01 (±0.4)	>1.75(±0.2)
Salt Scaling (Concrete G 30)	(g/m²)	12.2 (±0.3)	12.2 (±0.1)

Consumption of Material / Coverage

Concrete	(liter/m2)	0.15 – 0.25
0 181	(11) (0)	0.05
Cement Plaster	(liter/m2)	0.25 – 0.50
Sand-Lime or Clay Brick	(liter/m2)	0.40 - 0.70
	4	
Aerated Concrete	(liter/m2)	0.50 – 0.75
Cement Fiberboard	(liter/m2)	0.10 - 0.30
Natural Stone	(liter/m2)	0.05 – 0.75

These figures are intended as a guide and should not be used in preparing specifications.

Packaging	Top Grad 7388 Std Top Grad 7388 HP	20 liter Pail, 5 liter Tin or 1 Liter Tin 20 liter Pail, 5 liter Tin or 1 Liter Tin
Safety Information	Detailed safety information sheet, which can be obtained	n is contained in each material safety data safety ed from our sales offices

StorageTop Gard 7388 has a shelf life of at least 12 months when stored between 0 °C and 30 °C in the lightly closed original container. The containers must be protected against direct sunlight. The "Best use before end" date of each batch appears on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Approvals

In the USA, the following test have been performed on "Top Gard 7388"

DL Laboratories, New York, April 30, 1992	Building. Jetty & Bridge Structures External Surfaces	Federal Specification SS-W-110C "Water Repellent, Colorless Silicone Resin Base" Result: Water absorption: 0.2% (After 30 days)
Wiss, Janney ,Elstner Associates, Inc., Northbrook, Ilinois DL Laboratories, New York, April 30, 1992	Building. Jetty & Bridge Structures External Surfaces	Reduction of water absorption: 87% Reduction of chloride ion content: 89% Water vapor transmission: > 100% (within 7 days) Average penetration depth: 0.20 in.
Law Engineering, Atlanta, Georgia Wiss, Janney ,Elstner Associates, Inc., Northbrook, Ilinois DL Laboratories, New York, Jan, 1989	Building. Jetty & Bridge Structures External Surfaces	Northern climate: very slight scaling, 97.5% chloride reduction, no corrosion Southern climate: very slight scaling, 97.6% chloride reduction, no corrosion
Law Engineering, Atlanta, Georgia Wiss, Janney ,Elstner Associates, Inc., Northbrook, Ilinois DL Laboratories, New York, April 12, 1988	Building. Jetty & Bridge Structures External Surfaces	Reduction of water absorption: 85.1% Reduction of chloride ion content: 92.1% Water vapor transmission: 120.1%
Law Engineering, Atlanta, Georgia Wiss, Janney ,Elstner Associates, Inc., Northbrook, Ilinois DL Laboratories, New York, April 2, 1988	Building. Jetty & Bridge Structures External Surfaces	 @ "Resistance of concrete to Rapid Freezing and Thawing" (April 2, 1988) Result: Slight degree of scaling; durability factor 139% @ "Scaling Resistance of Concrete Surfaces" (May 6, 1988) Result: Slight degree of scaling Ontario Provincial Standard 1351.08.01 @ "Salt Scaling Acceptance Test" (December 14, 1988) 12.2.g/m² (allowed max. 800g/m²) visually no scaling detected
EBA Engineering Consultants Ltd., Edmonton, Alberta, Canada, September 20, 1988	Building. Jetty & Bridge Structures External Surfaces	Alberta DOT Specifications B388-90 "Evaluations of Sealers Used on Concrete Bridge Elements" Result: Initial Reduction of water absorption: 89.9% Reduction of water absorption after sandblasting: 82.6%

Approvals

The efficacy of "Top Gard WR 290" is borne out in the following laboratory report and test certificates. From Europe:

Centre Scientifique et Technique de la Construction, Brussels, Belgium	Commercial Building External Surfaces	Excellent Water Repellent of Top Gard 7388 in organic solvents
Eidgenossische Material prufungs- und Versuchsanstalt, Dubendorf, Switzerland. Test report no. 245/376, January 10 1985	Highway/Express Way Concrete Reinforced Road & Bridges External Area	Resistance to frost and road salt of concrete surfaces impregnated
Labor fur Preparation und Methodik, Bein am See, Switzerland Test Report No. A-4729, February 13, 1985	Jetty – Passenger, Marine & Commercial External Surfaces	Concerning the penetrative effectiveness of "impregnations with Top Gard 7388 and BS 44"
Bureau Veritas, Gennevilliers,France Test Report No. CN 53B950305E01, July 17, 1995:	Jetty – Passenger, Marine & Commercial External Surfaces	Concerning the penetrative effectiveness of impregnations with Top Gard 7388 and BS 44" Bureau Veritas, Gennevilliers, France

Handling Precautions

Wash off any silicone concentrate on the skin with plenty of water before it dries. During mixing and application ensure adequate ventilation since the silicone component contains active ingredient which is volatile and may cause eye watering in confined spaces. Avoid generation of airborne dust during mixing. Top Gard WR 290 silicone contains more than 10% Silane/siloxane and, therefore, in line with current legislation, is classified as irritating to eyes and skin. For this reason the following precautions should be observed:

Avoid contact with the skin and eyes; in case of contact with the eyes, rinse immediately with plenty of water and seek medical advice; wear suitable gloves and keep the product out of the reach of children.

The General Term & Conditions

All recommendations for use of our product, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us are based on the current state of our knowledge Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for this intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

The above mentioned details Specified key data are individually checked throughout, guarantee, and included in the certificates of Analysis (CoAs). & Typical key data are spot checked, the value are typical for the product and are indicated for information only. The values are not guaranteed or included in the CoAs.



LaMaCo System Sdn Bhd

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong, 05150 Alor Setar, Kedah. Malaysia

Tel: +60-4-771 1111 Fax: +60-4-772 4444

Http: <u>www.lamaco.com</u> Email: info@lamaco.com