

Polymer Patch Repair Mortar Cement Based

New Formula Two Component System

Description

Cem Strength 60 is a two component, thixotropic, Part A: Liquid Polymer with Part B: Powder Modified Cement mortar containing Pan Fiber & Silica Fume. **Cem Strength 60** cures to produce high strength mortar. **Cem Strength 60** exhibits high bond strength, greatly reduced water and carbon dioxide permeability and improved resistance to oils and chemicals. **Cem Strength 60** has excellent freeze/thaw resistance and good resistance to long term water immersion.

Uses

- ⊖ Fast repairs to horizontal or vertical concrete or mortar surfaces above and below ground level.
- ⊖ Filing / repair mortar for voids, honeycombed areas, etc
- ⊖ Repair of spalled concrete caused by reinforcement corrosion
- ⊖ Repairs with improved resistance to oils, sewage, chemicals, etc

Features and Benefits

- Easy to apply to clean, sound substrate in layers up to 20mm thick
- Two component system requiring only addition to clean water
- Compatible with the thermal expansion properties of concrete.
- Chloride free
- Non-corrosive to reinforcing steel
- Non-toxic, suitable for potable water
- Fibre to prevent micro crack
- Non-shrink

Mechanical of Properties Specification (Result tested at 25 °C)

Specific Gravity		Mixed - 2.01kg/litre
Mixing Ratio		3.50 kg (Part A) 25kg bag (Part B)
Pot Life		approx. 30 minutes at 20° C
Application Thickness		Min 3mm to 25mm thick
Application Temperature		Minimum 6° C
Compressive Strength	25 °C (1 days)	21.5 N/mm ²
Compressive Strength	25 °C (28 days)	32.2 N/mm ²
Flexural Strength	25 °C (28 days)	7.1 N/mm ²
Pull off Strength/core drilling		2.6 N/mm ²
Shrinkage	mm/m	-0.6
Bond on Concrete		>1.5 N/mm ²
Modulus of Elasticity		20000 N/mm ²

Method of Application

Surface Preparation

Precise and efficient surface preparation is essential to achieve the high adhesive qualities of **Cem Strength 60**. All concrete and mortar substrates must be sound, clean and free from oils, grease and surface contaminants. All loose materials and surface laitance must be removed. For large areas, grit or grit-water blasting or scabbling is recommended. For small areas and for "spot" repairs, needle gunning or brush-hammering is effective. The concrete or mortar substrate must have a minimum compressive strength of 20MPa. If in doubt test with a "Schmidt Hammer".

The prepared substrate should be thoroughly soaked with clean water until uniformly saturated but with no surface water. This condition is referred to as

saturated surface dry and care should be taken to remove any cement slurry or dust produced during surface preparation. The use of a "fan" shaped water jet is ideal. Steel reinforcements should have all traces of rust removed and be primed.

The **Cem Strength 60** and surrounding areas can be further treated with Cem Seal (Cement Base Waterproofing) to provide a water and carbonation resistant finish

Priming:
Concrete

Prior to application of **Cem Strength 60**, should be applied as a bonding bridge. Always work "wet on wet" on priming coats **Cem Strength Primer**.

Reinforcement

Two coats of **Cem Strength Primer** should be brush applied to the prepared steel.

Mixing

Cem Strength 60 should be mechanically mixed in a clean drum using a drill and paddle. A normal concrete mixer is NOT suitable. **Part A: Liquid Polymer** into a clean drum and add the **Part B: Powder Modified Cement** slowly while mixing. A minimum mixing time of 3 minutes is recommended to thoroughly blend the components with a maximum speed of 500 rpm to minimize air entrainment.

Application

Brush apply a bond coat onto the saturated surface dry substrate. Then, working wet on wet, work the mixed mortar well into the substrate, using a rendering rather than a placing technique to fill all pores and void. Compact well. Force material against the edge of the repair, working towards the centre. For repairs in excess of 20mm deep, apply in layers ensuring previous layers are well keyed and hardened. Finish lower layers with a heavy brush stipple to form a key for subsequent layers. If previous layers are over 48 hours old, needle gun the surface and dampen. Steel trowel the final coat if required.

The **Cem Strength 60** and surrounding areas can be further treated with Cem Seal (Cement Base Waterproofing) to provide a water and carbonation resistant finish

Curing

To achieve the full potential of any cement based material, curing is essential. In warm or windy weather, the use of polythene sheets or damp Hessian is necessary to protect the repair work.

Consumption Guide

Approximate 71 bags (25kg) per cubic metre. 1bag yields approx. 14 litres of mortar

Packing

28.5 kg set Part A: 3.50kg (Liquid) Part B: 25kg (Powder)

Storage Shelf Life

6 months from date of manufacture if stored in tightly sealed original packaging, in dry and cool enclosed area.



Cem Strength 60

Data Sheet

**Handling
Precautions**

For Health, safety and Environmental Recommendations, please consult and follow all instructions on the product Material Safety Data Sheet.

Important 1:

While the information and data sheet contained in this promotional literature are presented in good faith and believed to be reliable, they do not constitute a part of our terms and conditions of sales unless specifically incorporated in our Order acknowledgement. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data sheet are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data sheet or products can be used without infringing patent of third parties.

Important 2:

LAMACO Malaysia products are not guaranteed against defective materials and manufacture & are sold subject to its standard Terms & Conditions of sale, copies of which may be obtained on request. Whilst **LAMACO Malaysia** endeavors to ensure that any advice, recommendation, specification or information is accurate and correct, it cannot- because it has no direct or continuous control over where or how its products are applied – accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance any advice, specification, recommendation or information given by it.

Health & Safety

Some of the components of this product may be hazardous during mixing and application. Please consult the relevant Health & Safety Data Sheets, available from **LAMACO Malaysia** on request and sent with each delivery.



LAMACO SYSTEM SDN BHD

Co. No. 1033557-M

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong,
05150 Alor Setar, Kedah. Malaysia

Tel : +60-4-734 5555 Fax : +60-4-772 4444

Http : www.lamaco.com Email : info@lamaco.com



: +60 19 4486611 +60 19 4786611