

Characteristics

Functionality	<ul style="list-style-type: none"> • Extremely low viscosity and high capillary action • Deep penetration into substrate • Non-staining • Non-film forming • Reacts with dampness in the concrete forming a hydrophobic surface lining in the pores and capillaries • Reduces ingress of water and yet permits the concrete to breathe (water vapor transmission) • Reduces penetration of soot and grime • Resistant to chloride ingress
----------------------	---

Application	Apply by brush, roller or sprayer
--------------------	-----------------------------------

Area of use

- Facades
- Precast concrete elements
- Exposed concrete surfaces
- Bridge structures
- Tunnels
- Jetties

Technical data

Data	Criteria	Test Standard	Value	Unit
	Density		0.81	g/cm ³
	Viscosity @ 23°C	Rotation viscometer	10	mPas
	Flashpoint		44	°C
	Initial surface absorption @ 60 mins	BS 1881	0.002	ml/m ² /sec

The values stated are average values. Due to the use of natural raw material in our products, the actual value determined on an individual delivery may deviate slightly, without compromising product suitability.

Application

Substrate preparation	The surface to be impregnated must be clean, dry and free from oil, grease, dust, laitance and loose particles. Mechanical pretreatment is generally not necessary.
Coating procedure	Gem Coat DCI is supplied as a ready-to-use product. It can be applied in one or more applications by spray, roller or brush. On absorbent surface, increase rate of application until surface is completely saturated.
Consumption	The coverage rate is approximately 5 - 10m ² /litre per coat depending on the absorbency of the surface.
Application temperature	Minimum application temperature +8°C Maximum application temperature +45°C
Cleaning of tools	Tools must be cleaned immediately after use with thinner.

Delivery

Colour Colourless

Packing

Gem Coat DCI is available in 20 litre pail

Storage

Storage life / conditions The shelf life of Gem Coat DCI is approximately 12 months if stored in cool conditions.

Special notes

Safety Precautions

After full curing, Gem Coat DCI is physiologically harmless. Keep the product away from eyes, mouth and skin. Do not inhale vapour. Protective gloves should be used when handling these product. If skin contact occurs, cleaned immediately with soap and plenty of water. DO NOT use solvent. The use of goggles is recommended, however, should accidental eye contamination occur, rinse thoroughly with plenty of clean running water and seek medical immediately. Gem Coat DCI is flammable. DO NOT expose liquids or vapours to naked flames or other sources of ignition.

Technical Support Please consult Technical Service Department or the local sales office for further information and any site assistance required.

Disclaimer

Products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions. Whilst efforts are made to ensure that any advice, recommendation, specification or information may give is accurate and correct, it cannot accept any liability either directly or indirectly arising from the use of its products as it has no direct or continuous control over where or how the products are applied, whether or not in accordance with any advice, specification, recommendation or information given by it. If any product fails to conform, will replace the product at no cost to the buyer. Replacement of any products shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within six months from the date of the claimed breach. Buyers shall be solely responsible for determining the suitability of products for their intended use.

- Important 1:** While the information and data sheet contained in this promotional literature are presented in good faith and believed to be reliable, they do not constitute a part of our terms and conditions of sales unless specifically incorporated in our Order acknowledgement. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data sheet are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data sheet or products can be used without infringing patent of third parties.
- Important 2:** **LAMACO Malaysia** products are not guaranteed against defective materials and manufacture & are sold subject to its standard Terms & Conditions of sale, copies of which may be obtained on request. Whilst **LAMACO Malaysia** endeavors to ensure that any advice, recommendation, specification or information is accurate and correct, it cannot- because it has no direct or continuous control over where or how its products are applied – accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance any advice, specification, recommendation or information given by it.
- Health & Safety** Some of the components of this product may be hazardous during mixing and application. Please consult the relevant Health & Safety Data Sheets, available from **LAMACO Malaysia** on request and sent with each delivery.



LAMACO SYSTEM SDN BHD

Co. No. 1033557-M

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong,
05150 Alor Setar, Kedah, Malaysia

Tel : +60-4-734 5555 Fax : +60-4-772 4444

Http : www.lamaco.com Email : info@lamaco.com



: +60 19 4486611 +60 19 4786611